

SW SOLID

2 part water-based consolidating agent




CE marking:


→ EN 1504-2 (C) • Principles: MC-IR




TECHNICAL FEATURES



FIELD OF APPLICATION



APPLICATIONS



Description

SW SOLID is a water-based transparent bi-component epoxy cortical consolidating agent made up of:

- Component A: mixture of liquid epoxy prepolymers, additives and emulsifiers.
- Component B: copolymerization amines and additives.

The product has high penetrating capacity even on wet substrates.

After polymerization, SW SOLID develops an exceptional consolidating power and gives rise to a surface film with anti-dust and anti-oil power.

CE Marking

► EN 1504-2

SW SOLID meets the principles defined in EN 1504-9 ("Products and systems for the protection and repair of concrete structures: definitions, requirements, quality control and conformity assessment. General principles for use and systems") and the requirements of EN 1504-2 ("Concrete surface protection systems") for the class:

→ MC-IR

- For Principle 2 (MC) - Moisture control: 2.2 Coating (C), ZA.1e.
- For Principle 8 (IR) - Increasing Resistivity.

Field of application

SW SOLID is used for the realization of:

- Transparent anti-dust and anti-oil treatments with a glossy effect, on quartz-hardened concrete floors (with or without iron-oxide colouring) matured for at least ten days.
- Consolidating treatments for plasters or mortars without cohesion.
- Primer for the treatment of concrete floors before coating with film resins.
- Consolidating finishing treatment for polymer-cement trowel coatings, microcements and skim coats.
- Additive for mortars, skim coats and concretes to increase adhesion performance, mechanical strength, flexibility in interiors and exteriors.

Advantages

- SW SOLID has high impregnating characteristics and good chemical resistance.
- SW SOLID contains no solvents and is virtually odorless.
- SW SOLID gives rise to a vapor-permeable film.
- SW SOLID has a high resistance to atmospheric agents that makes it suitable for outdoor use.

SW SOLID

Specific preparation of the laying substrate

► Use as a dustproof

- Carry out a thorough cleaning of old surfaces with products suitable for the elimination of anything that may inhibit the adhesion and penetration of SW SOLID (greases, oils, paints, etc.). Normally a washing with STRIPPER and mechanical brushing are sufficient. At the end of the treatment, suck all the washing liquid from the substrate, rinse and wash with hard surface detergent and rinse thoroughly.

► Use as a consolidator for spatulated floors

- Sand the surface (if required by the application cycle) and carefully remove the dust by vacuuming.

► Use as a consolidator for spatulated floors

- Sand the surface (if required by the application cycle) and carefully remove the dust by vacuuming.

Product preparation

► Use as anti-dust

- Pour SW SOLID (A) into the comp container. B and mix with a professional mixer.
- Add 3 – 4 parts water for each part by weight of compound A+B.
- Mix well until you get a homogeneous milky liquid.
- Proceed with the installation.

► Use as a consolidator for spatulated floors

- Pour SW SOLID (A) into the comp container. B and mix with a professional mixer.
- Add 4 – 6 parts water for each part by weight of compound A+B.
- Mix well until you get a homogeneous milky liquid.
- Proceed with the installation.

► Use as an additive for cementitious mixtures

- Pour SW SOLID (A) into the comp container. B and mix with a professional mixer.
- Add the A+B mixture to the mixing water of the cement premix in a percentage between 3 and 10% of the weight of the water.
- Mix well until you get a homogeneous milky liquid.
- Use the mixture thus obtained to make the cement mixture.

► Use as a bonding primer for damp surfaces

- Pour SW SOLID (A) into the comp container. B and mix with a professional mixer.
- Proceed with the laying of the pure A+B mixture.

Product application

► Getting Started

- Make sure that the temperature of the substrate is at least +10°C.
- This product, once the A+B mixture is formed, shows no visible signs of deterioration with the passage of time: no heat development, no thickening (invisible pot-life). The absence of obvious symptoms, however, SW SOLID does not mean that no chemical reaction is taking place in the product. For this reason, it is important to use the compound no later than 90 minutes after mixing the two components.

► Use as anti-dust

- Apply in 2 coats with a short-haired roller.
- To obtain a strong anti-oil effect, apply a third coat (3 coats in total).

► Use as a consolidator for spatulated floors

- Apply directly to the surface in a single coat using a wax spreader.
- Complete the treatment with a finish (COAT LUX or MAT, SEAL WAX, SUPERMAT, see Technical Data Sheets) in accordance with the installation specifications.

SW SOLID

► Use as an additive for cementitious mixtures

- Use the mixture of water and SW SOLID to prepare the cementitious product according to the instructions indicated in the Technical Data Sheet of the latter and use it normally.

NOTE: Adding SW SOLID may change the machinability and setting time of the premix to which it is added.

► Use as a bonding primer for damp surfaces

- Apply with a roller in a single coat (the product must not be diluted).
- Overapply by the next day.

Consumption

type of application	minimum consumption	maximum consumption	u.m.	notes
As a dust-proofing agent, in 2 coats. 1 kg (A+B) + 3÷4 kg water.	100	100	g/m ²	(1)
As anti-oil, in 3 coats. 1 kg (A+B) + 4÷6 kg water.	150	150	g/m ²	(1)
As a consolidating agent for floors with polished plaster effect. 1 kg (A+B) + 4÷5 kg water.	40	60	g/m ²	(1)
As an additive for cementitious mixes, per 1 L of mixing water.	30	100	g/L	(1)
As a gripping base coat for damp surfaces.	150	200	g/m ²	(1)

(1) The consumption shown in the table is for the undiluted product.

Tool cleaning

- Fresh product: cleaning with water (also hydrowashing).
- Hardened product: mechanical removal, specific paint strippers (GEL STRIPPER or FLUID STRIPPER) or heat gun.

Useful tips for laying

- After 90 minutes of mixing the two components A and B, stop applying even if the product does not show signs of thickening.
- Do not use at temperatures below +10 °C.
- Mix components A and B according to the ratio indicated on the package and in this Technical Data Sheet (see Technical Data tab). In case of partial use of the package, weigh the two components with a precision scale.
- For diluted product: if there are deposits at the bottom of the container, it indicates that the product has not been sufficiently mixed. Continue mixing until perfect homogeneity is reached.
- Read the Safety Data Sheet carefully.

Technical Data

► PRODUCT IDENTIFICATION DATA			value
Density (comp. A) at 23 °C, 50%RH, EN ISO 1675	kg/L		1,081 ± 0,002
Density (comp. B) at 23 °C, 50%RH, EN ISO 1675	kg/L		1,040 ± 0,003
Density (A+B) at 23 °C, 50 %RH, EN ISO 1675	kg/L		1,071 ± 0,004
Appearance (Component A)	-		Milky viscous liquid
Appearance (Component B)	-		Clear straw yellow viscous liquid
pH (potentiometric method) at 23°C, A+B diluted 1:4 with water, ISO 4316	-		9.8 ± 0.2

SW SOLID

► APPLICATION DATA AND FINAL PERFORMANCE		value
Mixing ratio by weight (A:B)	-	2 : 1
Pot-life (viscosimetric), double viscosity A+B, EN ISO 9514	Min	60 ± 9
Application temperature	°C	from +10 to +40
Surface drying time (23°C, 50%RH), EN ISO 9117-3	Hours	2,0 ± 0,5
Full curing time (at 23°C, 50% RH)	days	7
Wear resistance – Taber method, grinding wheel CS17, 1000 rpm, load 1 kg, EN ISO 5470-1	Mg	110 ± 10
Shore D hardness (A+B, maturation 7 days at +23 °C, 50 %RH), EN ISO 868	-	(57 ± 3)°
Surface gloss, 60° gloss, 1 part of (A+B) + 2 parts of water on fibre cement, EN ISO 2813	-	75 ± 6
Resistance to UV and condensate cycles, cycle A (8 hours UVA-340 at 60°C + 4 hours condensation 50°C), 168 hours overall, yellowing measurement on RAL 9002, RE, ASTM D4329	-	15 ± 2
Resistance to UV and condensate cycles, cycle A (8 hours UVA-340 at 60°C + 4 hours condensate 50°C), 168 hours overall, opacification measurement on RAL 9002, Rgloss (EN ISO 2813 method), ASTM D4329	-	- 72 ± 5

► TECHNICAL DATA IN ACCORDANCE WITH EN 1504-2		value
Water vapour permeability, SD equivalent air thickness, porous substrate, EN ISO 7783	m	0,14 ± 0,05 (Class I)
Capillary absorption and water permeability, EN 1062-3	kg/(m ² ·√h)	0,08 ± 0,01
Capillary absorption and water permeability, EN 1062-3	kg/(m ² ·√h)	0,08 ± 0,01

► CHEMICAL RESISTANCE EN ISO 2812-3 (Evaluation of the results of chemical resistance tests: 1 = disintegration of the product, 5 = no alteration. For the complete scale see Tab. 1, Appendix A)		value
Hydrochloric acid 30% in water	-	1
Sulfuric acid 10% in water	-	1
Phosphoric acid 20% in water	-	1
Acetic acid 30% in water	-	1
Ammonia 15% in water	-	5
Soda (sodium hydroxide) 30% in water	-	5
Hydrogen peroxide 3.5% (12 volumes)	-	5
Mixture of acetic acid (1%) and hydrogen peroxide (0.5%) in water	-	3
Ethyl acetate	-	4
Denatured ethyl alcohol	-	4
Technical acetone	-	4

Product storage

- 24 months in the original closed packaging, in a dry, covered environment, protected from sunlight and at a temperature between +5°C and +35°C.
- Protect the product against frost.

Packaging

VARIANT	PACKAGE	ADR	PACKAGE / PALLET	COMPONENTS	NOTES
-	kit (A+B) - 3 kg	P*	72 kit	A = 2 kg (plastic bucket) B = 1 kg (plastic jar)	
-	kit (A+B) - 7,5 kg	P*	28 kit	A = 5 kg (plastic bucket) B = 2.5 kg (plastic bucket)	

ADR legend:

NO = NON-DANGEROUS goods

SW SOLID

P* = DANGEROUS goods packed in limited quantities (packed as per ADR Chapter 3.4)

Si = DANGEROUS Goods

LEGAL NOTES

The information contained in this Technical Data Sheet is based on the knowledge and experience gained by Nord Resine up to the date of its issue and is for indicative purposes only. It does not constitute a technical specification nor does it imply the assumption of any warranty, express or implied, or liability regarding the results obtainable, which depend on multiple factors beyond the control of Nord Resine.

It is the user's responsibility to verify in advance, also through suitable tests, the suitability of the product for the intended use, compatibility with the substrate, appropriate environmental application conditions, and the execution of the installation according to workmanship standards, assuming all liability arising from the use of the product and the final result of the works.

Nord Resine reserves the right to modify, at any time and without prior notice, product characteristics, packaging, contained quantities, and this technical documentation. Nord Resine products are intended exclusively for professional use.

This Technical Data Sheet cancels and replaces previous editions. Please check the latest and most updated revision at <https://nordresine.com/en/>

EDITION

Issue: 12.06.2014

Revision: